

TEROSON MS 9120 SF

June 2017

PRODUCT DESCRIPTION

TEROSON MS 9120 SF provides the following product characteristics:

Technology	Silane-modified polymer
Product Type	Car body sealant
Components	One-component
Cure	Humidity
Application	Assembly
Appearance	White, Grey, Black
Consistency	Pasty

TEROSON MS 9120 SF is a 1-component sealant based on silane modified polymers which crosslinks (cures) to an elastic material by absorbing moisture from the air. The skin formation and curing times are dependent on humidity and temperature, and the curing time also depends on joint depth. By increasing the temperature and moisture these times can be reduced; low temperature as well as low moisture retard the process. TEROSON MS 9120 SF is free of solvents, isocyanates, silicones and PVC, and has a neutral odour. It adheres well to a great variety of substrates without the use of primer and is also well compatible with overpainting using commercially available 1- or 2- component car repair paints. As long as the applied material is uncured, TEROSON MS 9120 SF is spotweldable. The sealant also demonstrates good UV resistance and can therefore be used for interior and exterior applications.

Application Areas:

TEROSON MS 9120 SF can be used for the following applications:

Seam and joint sealing in the following areas: vehicle repair, vehicle body and vehicle manufacture, railway waggon, container manufacture as well as for vehicle superstructure. TEROSON MS 9120 SF is the ideal undercoat material for the sprayable seam sealant TEROSON MS 9320 SF.

TECHNICAL DATA

Colour:	white, grey, black
Odour:	almost not perceptible when completely cured
Consistency:	paste
Density, g/cm ³	approx. 1.6
Curing mechanism:	humidity curing
Skin formation time (+23° C/50% RH), min*:	approx. 8
Cure rate, mm/24 hrs*:	approx. 5

Shore-A-hardness (DIN 53505):	approx. 50
Tensile strength (acc. to DIN 53504), MPa:	approx. 3
Elongation at break (acc. to DIN 53504), %:	approx. 250
Volume change (acc. to DIN 52451), %:	7
Application temperature, °C:	10 to 40
Paint compatibility:	Yes (see for: overpainting)
In service temperature range, °C:	-30 to 90
Short exposure (up to 1 h), °C:	120

* DIN 50014 standard climate: 23°C, 50% relative air humidity

DIRECTIONS FOR USE

Preliminary Statement:

Prior to application it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Adhesion:

Good adhesion to sheet metal (in degreased raw, phosphated, galvanized chromium treated or topcoated paint condition); stainless steel, brass, aluminium (untreated, anodized or painted); PC, polyester; on thermoplastic blend trials are recommended, roughening of the surfaces will result in an increase of adhesion in any case.

No adhesion to PE, PP, PTFE (e.g. Teflon®) and PMMA (e.g. Perspex®). Substrates not mentioned above should be subject to trials.

Pre-Treatment:

The substrates must be clean, dry, oil and grease free. For pretreatment TEROSON VR 20 is suitable.

Application:

TEROSON MS 9120 SF can directly be applied from cartridges employing standard air or hand operated guns. Low material temperatures of the sealant will lead to an increase of viscosity, resulting in a lower extrusion rate. This can be avoided by bringing the sealant up to room temperature prior to application. On cold substrates condensation water may form if the temperature drops below the dew point, what will also reduce adhesion.

Tip based on our practical experience:

With deep joints, TEROSON MS 9120 SF can be used as an



undercoat for the sprayable seam sealing material TEROSON MS 9320 SF which can be applied wet-on-wet to TEROSON MS 9120 SF.

Cleaning:

TEROSON VR 20 or TEROSON VR 40 is recommended for removing uncured TEROSON MS 9120 SF from application equipment. Cured material can only be removed mechanically.

Primer:

When primers are used (phosphate and 2-component epoxy resin primers are particularly suitable due to their dog corrosion protection and adhesion), these should be completely dry/have fully cured, before sealing or coating with TEROSON MS 9120 SF is carried out. On account of the great variety of systems available, we recommend that sufficient trials should always be carried out.

Fillers and primer fillers:

If, after repair of damages caused by an accident, the parts to be painted must be coated with a filler, primer filler or sprayable filling paste, these should ideally be applied before sealing or coating with TEROSON MS 9120 SF is carried out. If coating with a filler or primer filler shall be carried out only after TEROSON MS 9120 SF has been applied, this can be performed using special wet-on-wet systems. On account of the great variety of systems available, we recommend that sufficient trials should always be carried out.

Painting properties:

TEROSON MS 9120 SF can be painted with usual commercial available car paints immediately after it has formed skin. Early overpainting does not inhibit curing but slows down the curing process. Overpainting should be carried out within 3 days max. From the 4th day onwards, primer TEROSON 150 P Primer should be used before painting in order to achieve optimal adhesion.

Incompatibility:

TEROSON MS 9120 SF is not compatible with uncured 1C-polyurethane material. PU products must have completely cured until TEROSON MS 9120 SF is applied. TEROSON MS 9120 SF should have fully cured until it is coated with TEROSON WT R 2000 BK AQU. Also the material should not be treated with aromatic solvent systems, for example, TEROSON SB S 3000 or TEROSON RB R 2000 HS since this may cause the sealant to partially dissolve or swell.

Storage:

Shelf life:

Frost-Sensitive	under certain conditions (may crystallize; reversible at 40°C)
Recommended storage temperature, °C	10 to 25
Shelf-life	12 months

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

