

## BONDERITE C-NE 10300

October 2018

### PRODUCT DESCRIPTION

BONDERITE C-NE 10300 provides the following product characteristics:

<b>Technology</b>	Industrial Cleaner
<b>Product Type</b>	Neutral Cleaner
<b>Application</b>	Parts Cleaning
Concentration	10 to 30 g/l
Operating Temperature	20 to 60 °C spray process

BONDERITE C-NE 10300 is an aqueous neutral cleaner. It is composed of organic corrosion protection components, cleaning active agents and inhibitors. Change of colour is caused by raw material and has no impact on performance.

### Application Areas:

Cleaning after cutting, stamping or pressing and simultaneously passivating of steel, cast iron and aluminium work pieces, e.g in the metal working industry as well as in the manufacture of engines and transmissions. BONDERITE C-NE 10300 is used in spray processes, suitable for high pressure operations. It has very good demulsifying properties.

### TECHNICAL DATA

Appearance	clear, bright yellowish liquid
Density at 20°C, DIN 51757	~1.03 g/cm <sup>3</sup>
pH-value (1% solution):	~9.3

### DIRECTIONS FOR USE

#### Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

#### Bath Make-up:

Add the required amount carefully to the circulation system.

Concentration on steel and cast iron	10 to 30 g/L
Concentration on Aluminium	10 to 30 g/L

#### Operating Data:

Temperature	20 to 60°C
Duration of treatment	0.5 to 3 min

### Bath Control:

BONDERITE C-NE 10300 solution is controlled by the titration of total alkalinity.

Feed, mL	100 mL
Titration:	0.5 N hydrochloric or 0.5 N sulphuric acid
End point:	pH 3.6
Indicator:	Methylorange
Titration factor (TF):	2.1

- With a pipette transfer 100 mL bath solution into a clean 300 mL Erlenmeyer-flask.
- Add 4 to 5 drops of indicator.
- Titrate the solution with 0.5 N hydrochloric or 0.5 N sulphuric acid.
- The endpoint will be shown by a colour change from orange to red (pH: 3.6).
- Multiply the consumption of the acid solution with the titration factor (TF), to get the concentration in g/L
- Divide this by 10 to get the value in %.

### Additional Directions:

Corrosion protection is increased, if deionized water instead of tap water is used and the work pieces are stored at low relative air humidity and shielded against weather exposure.

### Classification:

Please refer to the corresponding **Material Safety Data**

**Sheets** for details on:

**Hazards identification**  
**Transport information**  
**Regulatory information**

### Storage:

Recommended Storage Temperature	0 to 35°C
Shelf-life, months	36
Frost-Sensitive	yes

**ADDITIONAL INFORMATION****Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

## Reference 1